

HEXPARKET PRODUCT INFORMATION

Junckers Hexparket is produced as untreated hexagonal tiles in 3 separate pieces, Fig. 1. Each tile is provided with a groove on all sides. Delivered with loose tongues, 180 mm of length.

Nominal Board Dimensions:

Thickness: 20.5 mm (± 0.2 mm) Size: 370 x 370 x 370 mm (± 0.2 mm)

Drying Methods: Kiln dried.

Moisture Content:

Oak: 8 % (± 2 %)

Black Oak: 9% (± 2 %)

Precision Engineering: Landing Deviation: 0.4 mm.




Fig. 1

PRODUCT RANGE

Wood Species	Tile size [mm]	Grade	Surface	Features
Oak Black Oak	20.5 x 370 x 370 x 370	Harmony	Untreated	-

TECHNICAL PROPERTIES

Resistance to Indentation	Oak 3.4 Hardness Brinell
Fire Classification	C _{fl} - S ₁ (DIN EN 13501-1: 2002)
Thermal Conduction: (Transmission Coefficient)	Approx. 0,17 W/mK
Heat Resistance	20.5 mm: Approx. 0.12 m ² K/W
Surface	Untreated: Final sanding to grit 150.

PACKING AND WEIGHT

The tiles are wrapped in polythene.

Tiles / m ²	Tiles / pack	m ² / pack	Kg / pack
8.44	8	0.95	14